

Milling | Endmills | Cutting conditions

Side milling (Contour line finish)

	Low Carbon - Alloy - Tool Steel									GG-GGG-GTW			Stainless steel			Aluminium - Mg			Ti Alloys		
	HB 150-250 500~800 N/mm ²			HB 20-30 800~1000 N/mm ²			HRC 30-40 1000~1300 N/mm ²			>HB 180 Non - Alloyed			HRC 20 400~700 N/mm ²			Non - Alloyed			HRC 40-50		
Vc	160 (m/min)			120 (m/min)			100 (m/min)			140 (m/min)			50 (m/min)			180 (m/min)			65 (m/min)		
Ø	Fz (mm)	S (min ⁻¹)	F (mm/min)	Fz (mm)	S (min ⁻¹)	F (mm/min)	Fz (mm)	S (min ⁻¹)	F (mm/min)	Fz (mm)	S (min ⁻¹)	F (mm/min)	Fz (mm)	S (min ⁻¹)	F (mm/min)	Fz (mm)	S (min ⁻¹)	F (mm/min)	Fz (mm)	S (min ⁻¹)	F (mm/min)
4	0,035	12.730	1.790	0,03	9.550	1.150	0,03	7.960	960	0,035	11.150	1.570	0,03	3.980	480	0,035	14.330	2.010	0,025	5.180	520
6	0,04	8.490	1.360	0,035	6.370	900	0,035	5.310	750	0,04	7.430	1.190	0,035	2.660	380	0,04	9.550	1.530	0,027	3.450	380
8	0,07	6.370	1.790	0,065	4.780	1.250	0,065	3.980	1040	0,7	5.580	1.570	0,065	1.990	520	0,07	7.170	2.010	0,031	2.590	330
10	0,1	5.090	2.040	0,08	3.820	1.230	0,08	3.190	1030	0,1	4.460	1.790	0,08	1.600	520	0,1	5.730	2.300	0,038	2.070	320
12	0,12	4.240	2.040	0,1	3.190	1.280	0,1	2.660	1070	0,12	3.720	1.790	0,1	1.330	540	0,12	4.780	2.300	0,045	1.730	320
16	0,13	3.180	1.660	0,12	2.390	1.150	0,12	1.990	960	0,13	2.790	1.460	0,12	1.000	480	0,13	3.590	1.870	0,052	1.300	280
20	0,15	2.550	1.530	0,12	1.910	920	0,12	1.600	770	0,15	2.230	1.340	0,12	800	390	0,15	2.870	1.730	0,059	1.040	250

ap x d

F(fz) correction

ap	Fakt.
0,5	1,0
1,0	0,7
1,5	0,5
2,0	0,3

ae
1xd

ap	Fakt.
0,5	0,7
1,0	1,0
1,5	0,7
2,0	0,5

ae
0,5xd

ap	Fakt.
0,5	1,3
1,0	1,2
1,5	1,0
2,0	0,8

ae
0,2xd

The above stated application data are as per RED marked parameters.